



Standard Test Method for Evaluating the Flexural Properties of Fire-Retardant Treated Softwood Plywood Exposed to Elevated Temperatures¹

This standard is issued under the fixed designation D5516; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method is designed to determine the effect of exposure to high temperatures and humidities on the flexure properties of fire-retardant treated softwood plywood. In this test method, plywood is exposed to a temperature of 77°C (170°F).

1.2 The purpose of the test method is to compare the flexural properties of fire-retardant treated plywood relative to untreated plywood. The results of tests conducted in accordance with this test method provide a reference point for estimating strength temperature relationships. This test method is intended to provide an accelerated test at elevated temperatures and controlled humidities of plywood sheathing treated with the same chemical formulation(s) and processing conditions as plywood used commercially.

1.3 The values stated in SI units are to be regarded as standard. The values given in parentheses are mathematical conversions to inch-pound units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

D9 Terminology Relating to Wood and Wood-Based Products

¹ This test method is under the jurisdiction of ASTM Committee D07 on Wood and is the direct responsibility of Subcommittee D07.07 on Fire Performance of Wood.

Current edition approved May 15, 2009. Published June 2009. Originally approved in 1991 as E20–91. Last previous edition approved in 2003 as D5516–03. DOI: 10.1520/D5516-09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D1165 Nomenclature of Commercial Hardwoods and Softwoods

D2915 Practice for Sampling and Data-Analysis for Structural Wood and Wood-Based Products

D3043 Test Methods for Structural Panels in Flexure

D6305 Practice for Calculating Bending Strength Design Adjustment Factors for Fire-Retardant-Treated Plywood Roof Sheathing

E84 Test Method for Surface Burning Characteristics of Building Materials

E176 Terminology of Fire Standards

2.2 Other Standards:

AWPA C-27 Plywood-Fire Retardant Treatment by Pressure Processes³

NFPA 703 Standard for Fire Retardant Impregnated Wood and Fire Retardant Coatings for Building Materials⁴

PS 1 U.S. Product Standard for Structural Plywood⁵

PS 2 U.S. Product Standard for Wood-Based Structural Use Panels⁵

3. Terminology

3.1 *Definitions*—Definitions used in this test method are in accordance with Terminologies **D9** and **E176** and Nomenclature **D1165**.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *depth of beam*—that dimension of the beam which is perpendicular to the span and parallel to the direction in which the load is applied.

3.2.2 *span*—the total distance between the centerline of supports providing the reactions on which a beam is supported to accommodate a transverse load.

3.2.3 *span-depth ratio*—the numerical ratio of span divided by beam depth.

³ Available from American Wood Protection Association (AWPA), P.O. Box 361784, Birmingham, AL 35236-1784, <http://www.awpa.com>.

⁴ Available from National Fire Protection Association (NFPA), 1 Batterymarch Park, Quincy, MA 02169-7471, <http://www.nfpa.org>.

⁵ Available from the U.S. Department of Commerce, 1401 Constitution Ave., NW Washington, DC 20230, <http://ts.nist.gov/Standards/Conformity/vps.cfm>.