



Standard Test Method for Performing Laboratory Direct Shear Strength Tests of Rock Specimens Under Constant Normal Force¹

This standard is issued under the fixed designation D 5607; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope *

1.1 This test method establishes requirements and laboratory procedures for performing direct shear strength tests on rock specimens. It includes procedures for both intact rock strength and sliding friction tests which can be performed on specimens that are homogeneous, or have planes of weakness, including natural or artificial discontinuities. Examples of an artificial discontinuity include a rock-concrete interface or a lift line from a concrete pour. Discontinuities may be open, partially or completely healed or filled (that is, clay fillings and gouge). Only one discontinuity per specimen can be tested. The test is usually conducted in the undrained state with an applied constant normal load. However, a clean, open discontinuity may be free draining, and, therefore, a test on a clean, open discontinuity could be considered a drained test. During the test, shear strength is determined at various applied stresses normal to the sheared plane and at various shear displacements. Relationships derived from the test data include shear strength versus normal stress and shear stress versus shear displacement (shear stiffness).

NOTE 1—The term “normal force” is used in the title instead of normal stress because of the indefinable area of contact and the minimal relative displacement between upper and lower halves of the specimen during testing. The actual contact areas during testing change, but the actual total contact surface is unmeasurable. Therefore nominal area is used for loading purposes and calculations.

NOTE 2—Since this test method makes no provision for the measurement of pore pressures, the strength values determined are expressed in terms of total stress, uncorrected for pore pressure.

1.2 This standard applies to hard rock, soft rock, and concrete.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- D 653 Terminology Relating to Soil, Rock, and Contained Fluids²
- D 2216 Test Method for Laboratory Determination of Water (Moisture) Content of Soil and Rock²
- D 3740 Practice for Minimum Requirements for Agencies Engaged in the Testing and/or Inspection of Soil and Rock Used in Engineering Design and Construction²
- E 4 Practices for Load Verification of Testing Machines³
- E 122 Practice for Choice of Sample Size to Estimate the Average Quality of a Lot or Process⁴

3. Terminology

3.1 For common definitions of terms used in this standard, refer to Terminology D 653.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *apparent stress*—nominal stress, that is, external load per unit area. It is calculated by dividing the externally applied load by the nominal area.

3.2.2 Asperity:

3.2.2.1 *quality*—the roughness of a surface.

3.2.2.2 *feature*—a surface irregularity ranging from sharp or angular to rounded or wavy.

3.2.2.3 *asperities*—the collection of a surface’s irregularities that account for the surface’s roughness.

3.2.3 Discontinuity:

3.2.3.1 An abrupt change, interruption, or break in the integrity or physical properties of rock, such as a bedding plane, fracture, cleavage, crack, joint, or fault.

3.2.3.2 A *gapped discontinuity* consists of opposing rock surfaces separated by an open or filled space. A *tight discontinuity* consists of opposing rock surfaces in intimate and generally continuous contact; it may be valid to treat such a discontinuity as a single surface.

3.2.3.3 A discontinuity’s opposing rock surfaces may be *planar* to *nonplanar* and *matching* to *misfit*.

3.2.4 *intact shear strength*—the peak shear resistance (in

¹ This test method is under the jurisdiction of ASTM Committee D18 on Soil and Rock and is the direct responsibility of Subcommittee D18.12 on Rock Mechanics. Current edition approved Jan. 10, 2002. Published April 2002. Originally published as D 5607 – 94. Last previous edition D 5607 – 95.

² Annual Book of ASTM Standards, Vol 04.08.

³ Annual Book of ASTM Standards, Vol 03.01.

⁴ Annual Book of ASTM Standards, Vol 14.02.