



Standard Specification for Extruded and Monomer Cast Shapes Made from Nylon (PA)¹

This standard is issued under the fixed designation D5989; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

This specification is intended to be a means of calling out plastic products used in the fabrication of end items or parts.

1. Scope*

1.1 This specification covers requirements and test methods for the material, dimensions, and workmanship, and the properties of extruded and cast sheet, plate, rod and tubular bar, excluding pipe and fittings, manufactured from nylon or monomers.

1.2 The properties included in this specification are those required for the compositions covered. Requirements necessary to identify particular characteristics important to specialized applications are described by using the classification system given in Section 4.

1.3 This specification allows for the use of recycled plastics (as defined in Guide D7209).

1.4 The values stated in English units are regarded as standard. The values in parentheses are for information only.

1.5 The following precautionary caveat pertains only to the test method portions of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no known ISO equivalent to this standard.

NOTE 2—This specification is intended to replace Federal Standard LP-410A and PS 50.

2. Referenced Documents

2.1 ASTM Standards:²

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials.

Current edition approved July 1, 2014. Published July 2014. Originally approved in 1998. Last previous edition approved in 2014 as D5989 – 14. DOI: 10.1520/D5989-14A.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D256 Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics

D638 Test Method for Tensile Properties of Plastics

D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials

D883 Terminology Relating to Plastics

D3892 Practice for Packaging/Packing of Plastics

D6779 Classification System for and Basis of Specification for Polyamide Molding and Extrusion Materials (PA)

D7209 Guide for Waste Reduction, Resource Recovery, and Use of Recycled Polymeric Materials and Products

2.2 Federal Standard:³

LP-410A Nylon Stock Shapes

3. Terminology

3.1 Definitions:

3.1.1 *regrind (plastic)*, *n*—a product or scrap such as sprues, runners and edge trim that have been reclaimed by shredding and granulating for use in-house.

3.1.2 For definitions of other technical terms pertaining to plastics used in this specification, see Terminology D883 or Guide D7209.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *finished product (F)*, *n*—product that meets the dimensional criteria of Table 1, Table 2, Table 3, or Table 4 of this specification.

3.2.2 *monomer-cast nylon*, *n*—nylon polymer prepared by polymerization of epsilon-caprolactam or lauryllactam monomer.

3.2.3 *oversize product (O)*, *n*—product that meets only the designated dimensional criteria of Table 2 or Table 4.

3.2.4 *plate*, *n*—flat stock greater than 3/8 in. (9.5 mm).

³ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, <http://www.access.gpo.gov>.

*A Summary of Changes section appears at the end of this standard