



Standard Specification for Expandable Foam Adhesives for Fastening Gypsum Wallboard to Wood Framing¹

This standard is issued under the fixed designation D6464; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Editorial changes were made throughout in November 2009.

1. Scope*

1.1 This specification establishes minimum performance requirements for determining strength, aging, and working properties of expandable foam adhesives intended for bonding back surfaces of gypsum wallboards of all thicknesses to wood framing. Minimum physical and performance requirements are specified for all measured properties of adhesives and adhesive bonds.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C1396/C1396M Specification for Gypsum Board
D905 Test Method for Strength Properties of Adhesive Bonds in Shear by Compression Loading
D907 Terminology of Adhesives
E4 Practices for Force Verification of Testing Machines
E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods

3. Terminology

3.1 *Definitions*—Many terms in this specification are defined in Terminology D907.

¹ This specification is under the jurisdiction of ASTM Committee D14 on Adhesives and is the direct responsibility of Subcommittee D14.70 on Construction Adhesives.

Current edition approved Nov. 1, 2009. Published December 2009. Originally approved in 1999. Last previous edition approved in 2003 as D6464 - 03a^{ε1}. DOI: 10.1520/D6464-03A09E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *expandable foam adhesive, n*—any polymer that expands during delivery or cure to fill the space between substrates.

4. Significance and Use

4.1 This specification applies to expandable foam adhesives used to bond the back surface of gypsum wallboard to Douglas-fir dimensional lumber or other lumber species of equivalent bonding qualities capable of meeting the test requirements.

4.2 The specification establishes the minimum strength requirements of the bond for the selected assembly materials.

4.3 The adhesive is not considered a substitute for mechanical fasteners. Fasteners will be required to restrict expansion of the foam adhesive while it cures. The recommended fastening schedule must appear in the manufacturer's application instructions.

4.4 The tests are suitable for product performance certification and quality control programs, and can be useful to the general public, adhesive manufacturers, distributors, specifiers, architects, contractors, testing laboratories and other businesses and professionals.

4.5 The results do not include all possible conditions, which may occur during final assembly, but indicate a set of performance characteristics for laboratory controlled bonding variables.

5. Adhesive Physical Property Requirements

5.1 *Open Assembly Time*—These adhesives have a distinct open assembly time and this time must be agreed upon by the user and the manufacturer.

5.2 *Storage Life*—The adhesive shall remain serviceable and meet all the requirements of this specification for not less than six months after delivery, when stored in original unopened containers at temperatures ranging from 40 to 85°F (4 to 30°C).

*A Summary of Changes section appears at the end of this standard