



Standard Guide for Selection of Asphalt Used in Built-Up Roofing Systems¹

This standard is issued under the fixed designation D 6510; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 The purpose of this guide is to provide advice for the selection of asphalt used in the construction of built-up roofing (BUR). This guide does not address the use of asphalt in waterproofing, cold-applied, or modified bituminous roofing.

1.2 Reinforcements considered for use with roofing asphalt include ply sheets, (see Specifications D 226, D 2178, and D 5726), base sheets (see Specifications D 2626, D 4601, and D 4897), and cap sheets (see Specification D 3909). They consist of glass, organic, or synthetic fibers.

1.3 The use of asphalt in the placement of vapor retarders and rigid roof insulation also is addressed.

2. Referenced Documents

2.1 ASTM Standards:

D 92 Test Method for Flash and Fire Points by Cleveland Open Cup²

D 226 Specification for Asphalt-Saturated Organic Felt Used in Roofing and Waterproofing³

D 312 Specification for Asphalt Used in Roofing³

D 1079 Terminology Relating to Roofing, Waterproofing, and Bituminous Materials³

D 1863 Specification for Mineral Aggregate Used in Built-Up Roofs³

D 2178 Specification for Asphalt Glass Felt Used in Roofing and Waterproofing³

D 2626 Specification for Asphalt-Saturated and Coated Organic Felt Base Sheet Used in Roofing³

D 3791 Practice Evaluating the Effects of Heat on Asphalts³

D 3909 Specification for Asphalt Roll Roofing (Glass Felt) Surfaced with Mineral Granules³

D 4601 Specification for Asphalt-Coated Glass Fiber Base Sheet Used in Roofing³

D 4897 Specification for Asphalt-Coated Glass-Fiber Venting Base Sheet Used in Roofing³

D 5726 Specification for Thermoplastic Fabrics Used in Hot-Applied Roofing and Waterproofing³

3. Terminology

3.1 *Definitions*—For definitions of terms used in this guide, see Terminology D 1079.

3.2 For a discussion of EVT, refer to NRCA Bulletin 2-91 (or the current edition of the NRCA Roofing and Waterproofing Manual).⁴

4. Significance and Use

4.1 This guide supersedes the slope guidelines of Appendix X1 of Specification D 312.

4.2 Hot-applied roofing asphalt serves both as the waterproofing agent and adhesive for construction of built-up roofing membranes. There are many variables that may affect the performance of BUR membranes. This guide provides general specification guidelines for the asphalt only.

5. General Considerations

5.1 *Durability*—Specification D 312 describes four types of asphalt. In general, the softest (least oxidized) asphalt is considered most durable. The accepted rule is to select the softest bitumen commensurate with the slope, consistent with the other variables.

5.2 When the EVT guidelines are followed the asphalt application rate can be expected to fall within the ranges of 1.0 to 2.0 kg/m² (20 to 40 lb/100 ft²).

5.3 Table 1 provides general recommendations for the use of the various types of Specification D 312 asphalt.

5.3.1 In hotter climates, harder (higher viscosity) bitumens are chosen to minimize slippage potential. Table 2 provides some general guidance for proper asphalt selection whenever solar exposure is considered.

5.4 Recommended slope guidelines for the respective Specification D 312 asphalts are as follows:

5.4.1 Type I asphalts are relatively susceptible to flow. They generally are used in aggregate-surfaced roofs on inclines up to 2 % (¼ in./ft) slope.

5.4.2 Type II asphalts are moderately susceptible to flow at roof temperatures. They are sometimes used in built-up roof construction on inclines from approximately 2 % (¼ in./ft) slope to 8.3 % (1 in./ft) slope.

5.4.3 Type III asphalts are relatively nonsusceptible to flow. They are used in built-up roof construction on inclines from

¹ This guide is under the jurisdiction of ASTM Committee D-8 on Roofing, Waterproofing, and Bituminous Materials and is the direct responsibility of Subcommittee D08.20 on Roofing Membrane Systems.

Current edition approved Jan. 10, 2000. Published March 2000.

² *Annual Book of ASTM Standards*, Vol 05.01.

³ *Annual Book of ASTM Standards*, Vol 04.04.

⁴ NRCA Roofing and Waterproofing Manual, Current Edition, *Use of EVT* (or NRCA Bulletin 2-91), available from the National Roofing Contractors Association, Rosemont, IL.