



Designation: D6553 – 23

Standard Test Method for Coolant Compatibility of Way Lubricants¹

This standard is issued under the fixed designation D6553; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This test method measures the ability of single-use way lubricants to separate from metalworking coolants (synthetic coolants, semisynthetic coolants, and soluble oils) or other alkaline aqueous fluids.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* For specific warning statements, see Section 7.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D1193 Specification for Reagent Water

D1401 Test Method for Water Separability of Petroleum Oils and Synthetic Fluids

D4057 Practice for Manual Sampling of Petroleum and Petroleum Products

D4175 Terminology Relating to Petroleum Products, Liquid Fuels, and Lubricants

3. Terminology

3.1 *Definitions:*

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee D02.L0.01 on Metal Removal Fluids and Lubricants.

Current edition approved March 1, 2023. Published April 2023. Originally approved in 2000. Last previous edition approved in 2016 as D6553 – 00 (2016). DOI: 10.1520/D6553-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.1 For definitions of terms used in this test method, refer to Terminology D4175.

3.1.2 *cuff, n*—a layer between the way oil layer and the coolant or buffer layer that contains significant amounts of both. In describing this intermediate layer, *cuff* is preferred to *emulsion* since many of the coolants are themselves emulsions.

4. Summary of Test Method

4.1 This test procedure is essentially identical to Test Method D1401, with the actual coolant or an alkaline buffer replacing the distilled water of that test method. A 40 mL sample and 40 mL of either actual coolant or a pH 9.0 buffer solution (see Note 1) are stirred for 5 min at 54 °C (see Note 2) in a graduated cylinder. The time required for the separation of the emulsion thus formed is recorded. If complete separation or emulsion reduction to 3 mL or less does not occur after standing for 30 min, the volumes of oil (or fluid), water, and emulsion remaining at the time are reported.

NOTE 1—Distilled water is not a satisfactory aqueous phase for testing the ability of way lubricants to separate from coolants because distilled water gives different results from coolants. The best procedure is to use the actual coolant that the way lubricant will contaminate. A buffer solution of pH 9.0 may be used in place of a specific coolant to predict the separability from alkaline coolants in general.

NOTE 2—It is recommended, however, that the test temperature be raised to 82 °C $\pm$ 1 °C when testing way lubricants more viscous than 90 cSt (mm²/s) at 40 °C.

5. Significance and Use

5.1 In the normal use of a way lubricant in a machine tool, the way lubricant eventually becomes a contaminant that may emulsify into the coolant. It is generally desirable to remove this contaminant by skimming; otherwise, the coolant lifetime may be significantly shortened. This test method provides a guide for determining the separability characteristics of way lubricants that are expected to get into aqueous alkaline metalworking coolants. It is used for specification of new oils and might be useful in monitoring of in-service oils.

6. Apparatus

6.1 *Cylinder*, 100 mL, graduated from 5 mL to 100 mL in 1.0 mL divisions, made of glass, heat-resistant glass, or a chemical equivalent. The inside diameter shall be no less than 27 mm and no more than 30 mm throughout its length, measured from the top to a point 6 mm from the bottom of the

*A Summary of Changes section appears at the end of this standard