



Designation: D6916 – 18 (Reapproved 2024)

Standard Test Method for Determining the Shear Strength Between Segmental Concrete Units (Modular Concrete Blocks)¹

This standard is issued under the fixed designation D6916; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method is used to determine the shear strength between two layers of segmental concrete block units used in construction of reinforced soil retaining walls. The test is carried out under conditions determined by the user that reproduce the facing system at full scale. The results of a series of tests are used to define a relationship between shear strength developed between segmental concrete units and normal load.

1.2 This is a performance test used to determine properties for design of retaining wall systems utilizing segmental concrete units and soil reinforcing geosynthetics, either geotextiles or geogrids. The test is performed on a full-scale construction of the facing system and may be run in a laboratory or the field.

1.3 The values stated in SI units are regarded as the standard. The values stated in inch-pound units are provided for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

D448 Classification for Sizes of Aggregate for Road and Bridge Construction

D4354 Practice for Sampling of Geosynthetics and Rolled Erosion Control Products (RECPs) for Testing
D4439 Terminology for Geosynthetics
D4595 Test Method for Tensile Properties of Geotextiles by the Wide-Width Method
D6637/D6637M Test Method for Determining Tensile Properties of Geogrids by the Single or Multi-Rib Tensile Method

3. Terminology

3.1 Definitions:

3.1.1 *displacement criteria, n*—a user-prescribed maximum movement, mm (in.), of the top segmental concrete unit out from the back of lower segmental concrete units.

3.1.2 *geosynthetic, n*—a planar product manufactured from polymeric material used with soil, rock, earth, or other geotechnical engineering-related material as an integral part of a manmade project, structure, or system. **D4439**

3.1.3 *granular infill, n*—coarse-grained soil aggregate used to fill the voids in and between segmental concrete units.

3.1.4 *peak shear strength, n*—the maximum shear capacity between segmental concrete units.

3.1.5 *segmental concrete depth, n*—the segmental concrete unit dimension perpendicular to the wall face.

3.1.6 *segmental concrete unit (modular concrete block), n*—a concrete unit manufactured specifically for mortarless, dry-stack retaining wall construction.

3.1.7 *segmental concrete unit width, n*—the segmental concrete unit dimension parallel to the wall face.

3.2 For definitions of other terms relating to geosynthetics, refer to Terminology **D4439**.

4. Summary of Test Method

4.1 In this test method, segmental concrete units are assembled in two rows (layers). The bottom row is laterally restrained. The top row is loaded vertically to a constant surcharge load, and the interface is sheared at a constant rate of displacement until a drop of load after the peak load occurs. The test may be run with the geosynthetic reinforcement sandwiched between the two rows of segmental concrete units

¹ This test method is under the jurisdiction of ASTM Committee **D35** on Geosynthetics and is the direct responsibility of Subcommittee **D35.01** on Mechanical Properties.

Current edition approved Nov. 1, 2024. Published November 2024. Originally approved in 2003. Last previous edition approved in 2018 as D6916 – 18. DOI: 10.1520/D6916-18R24.

² For referenced ASTM standards, visit the ASTM Web Site, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM web site.