

Standard Specification for Polyethylene Stay In Place Form System for End Walls for Drainage Pipe¹

This standard is issued under the fixed designation D7082; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification addresses the requirements for polyethylene stay in place forms for end walls or head walls for use with standard storm drainage systems.

1.2 The wall form system consists of a base wall form, a cap, an optional riser to adjust the height of the wall above the pipe, and an optional adaptor to adjust the pipe opening to accommodate smaller pipe sizes.

1.3 The form system is manufactured using the rotational molding process and is available in different colors.

1.4 The values stated in SI units are to be regarded as the standard, the inch-pounds in parentheses are given for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory requirements prior to use.*

NOTE 1—There is no known ISO equivalent to this standard.

2. Referenced Documents

2.1 ASTM Standards:²

- D638 Test Method for Tensile Properties of Plastics
- D648 Test Method for Deflection Temperature of Plastics Under Flexural Load in the Edgewise Position
- D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials
- D883 Terminology Relating to Plastics
- D1238 Test Method for Melt Flow Rates of Thermoplastics by Extrusion Plastometer

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.24 on Plastic Building Products.

Current edition approved Oct. 1, 2015. Published October 2015. Originally approved in 2004. Last previous edition approved in 2010 as D7082 - 04(2010). DOI: 10.1520/D7082-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- D1505 Test Method for Density of Plastics by the Density-Gradient Technique
- D1600 Terminology for Abbreviated Terms Relating to Plastics
- D1693 Test Method for Environmental Stress-Cracking of Ethylene Plastics
- D4883 Test Method for Density of Polyethylene by the Ultrasound Technique

3. Terminology

3.1 Definitions:

3.1.1 Definitions used in this specification are in accordance with definitions in Terminology D883 and abbreviations in accordance with Terminology D1600 unless otherwise indicated.

3.1.2 *end wall*—a wall installed at the outlet of a storm drainage pipe.

3.1.3 *head wall*—a wall installed at the inlet of a storm drainage pipe.

4. Ordering Information

- 4.1 Number and color of base wall forms,
- 4.2 Number and color of riser forms,
- 4.3 Number and color of caps, and
- 4.4 Number, color and size of adaptors.

5. Materials and Manufacture

5.1 The material used shall be a polyethylene meeting the criteria in Table 1.

5.2 Only virgin materials shall be used.

5.3 This product shall be manufactured using a rotational molding process.

6. Requirements

6.1 Wall System Description:

6.1.1 Base wall form is hollow with opening at the top to accept fill material and designed to accept either cap or riser section. Base wall has opening in the center for pipe and adaptors as needed. Pipe is secured to base wall form with galvanized screws. (See Fig. 1.)

*A Summary of Changes section appears at the end of this standard