



Designation: D7121 – 05 (Reapproved 2024)

Standard Test Method for Rubber Property—Resilience Using Schob Type Rebound Pendulum¹

This standard is issued under the fixed designation D7121; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a means of determining the resilience of rubber, within a range of impact strain and strain rate, by means of the impacting and measuring apparatus conforming to the requirements described in this test method.

1.2 This test method is applicable to thermoset rubbers and thermoplastic elastomers, the hardness of which, at the specified test temperatures, lies between 30 and 85 IRHD (see Test Method [D1415](#)) or A/30 and A/85 (see Test Method [D2240](#)). It may also be applicable to some polyester, polyether foam, and plastic foam materials.

1.3 All materials, instruments, or equipment used for the determination of mass, force, or dimension shall have traceability to the National Institute for Standards and Technology, or other internationally recognized organization parallel in nature.

1.4 The values stated in SI units are to be regarded as standard. The values given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of ASTM Committee [D11](#) on Rubber and Rubber-like Materials and is the direct responsibility of Subcommittee [D11.10](#) on Physical Testing.

Current edition approved May 1, 2024. Published June 2024. Originally approved in 2005. Last previous edition approved in 2018 as D7121 – 05 (2018). DOI: 10.1520/D7121-05R24.

2. Referenced Documents

2.1 *ASTM Standards:*²

- [D832 Practice for Rubber Conditioning For Low Temperature Testing](#)
- [D1349 Practice for Rubber—Standard Conditions for Testing](#)
- [D1415 Test Method for Rubber Property—International Hardness](#)
- [D2240 Test Method for Rubber Property—Durometer Hardness](#)
- [D3182 Practice for Rubber—Materials, Equipment, and Procedures for Mixing Standard Compounds and Preparing Standard Vulcanized Sheets](#)
- [D3183 Practice for Rubber—Preparation of Pieces for Test Purposes from Products](#)
- [D4483 Practice for Evaluating Precision for Test Method Standards in the Rubber and Carbon Black Manufacturing Industries](#)

3. Summary of Test Method

3.1 This test method describes the determination of resilience, expressed as percentage resilience or rebound resilience, by a Schob Type pendulum rebound device as a ratio between the returned and applied energy when a spherically terminated mass impacts a test specimen under the conditions specified in this test method.

3.2 Resilience of the materials described is infinitely variable. It varies with temperature, strain rate (specifically related to the velocity of the indenter), and strain energy (specifically related to the mass of the indenter, coupled with velocity).

3.3 The variable factors, described and defined in this test method, will have effects on the outcomes of test results.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.