



Designation: D7527 – 24

Standard Test Method for Measurement of Antioxidant Content in Lubricating Greases by Linear Sweep Voltammetry¹

This standard is issued under the fixed designation D7527; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the voltammetric determination of antioxidants in new or in-service lubricating greases in concentrations from 0.0075 % by weight up to concentrations found in new greases by measuring the amount of current flow at a specified voltage in the produced voltammogram.

1.2 This test method is intended to monitor the antioxidant content in lubricating greases; it cannot be applied for lubricating greases that do not contain antioxidants.

1.3 This test method is designed to allow the user to monitor the antioxidant depletion rate of in-service greases through its life cycle as part of condition monitoring programs. This test method is performed in order to collect and trend early signs of deteriorating lubricant grease, and it may be used as a guide for the direction of any required maintenance activities. This will ensure a safe, reliable, and cost-effective operation of the monitored plant equipment.

1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee D02.09.0E on Oxidation of Greases.

Current edition approved June 15, 2024. Published July 2024. Originally approved in 2010. Last previous edition approved in 2018 as D7527 – 10 (2018). DOI: 10.1520/D7527-24.

2. Referenced Documents

2.1 ASTM Standards:²

- D942 Test Method for Oxidation Stability of Lubricating Greases by the Oxygen Pressure Vessel Method
- D1193 Specification for Reagent Water
- D4057 Practice for Manual Sampling of Petroleum and Petroleum Products
- D4175 Terminology Relating to Petroleum Products, Liquid Fuels, and Lubricants
- D5483 Test Method for Oxidation Induction Time of Lubricating Greases by Pressure Differential Scanning Calorimetry
- D6300 Practice for Determination of Precision and Bias Data for Use in Test Methods for Petroleum Products, Liquid Fuels, and Lubricants
- D6810 Test Method for Measurement of Hindered Phenolic Antioxidant Content in Non-Zinc Turbine Oils by Linear Sweep Voltammetry
- D6971 Test Method for Measurement of Hindered Phenolic and Aromatic Amine Antioxidant Content in Non-zinc Turbine Oils by Linear Sweep Voltammetry
- D7718 Practice for Obtaining In-Service Samples of Lubricating Grease

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms used in this test method, refer to Terminology D4175.

4. Summary of Test Method

4.1 A measured quantity of sample is weighed into a vial containing a measured quantity of acetone based electrolyte solution and containing a layer of sand. When the vial is shaken, the dissolved antioxidants and other solution soluble

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard