



Designation: D 3410/D 3410M – 9503

Standard Test Method for Compressive Properties of Polymer Matrix Composite Materials with Unsupported Gage Section by Shear Loading¹

This standard is issued under the fixed designation D 3410/D 3410M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method determines the in-plane compressive properties of polymer matrix composite materials reinforced by high-modulus fibers. The composite material forms are limited to continuous-fiber or discontinuous-fiber reinforced composites for which the elastic properties are specially orthotropic with respect to the test direction. This test procedure introduces the compressive load force into the specimen through shear at wedge grip interfaces. This type of load force transfer differs from the procedure in Test Method ~~D 5467~~ D 695 where compressive load force is transmitted into the specimen by end-loading, Test Method D 6641/D 6641M where compressive force is transmitted by combined shear and end loading, and Test Method D 5467/D 5467M where compressive force is transmitted by subjecting a honeycomb core sandwich beam with thin skins to four-point bending, or Test Method ~~D 695~~ where compressive load is transmitted into the specimen by end-loading, bending.

1.2 This ~~procedure~~ test method is applicable ~~primarily to laminates~~ composites made from unidirectional tape, wet-tow placement, textile (for example, fabric), short fibregs, or similar product forms. ~~Other~~ Some product forms may require deviations from the test method.

~~1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.~~

~~1.4 The~~

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text the inch-pounds units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

NOTE 1—Additional procedures for determining compressive properties of resin-matrix composites may be found in Test Methods D 695, D 5467/D 5467M, and ~~D 695~~, D 6641/D 6641M.

~~1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.~~

2. Referenced Documents

2.1 ASTM Standards:

¹ This specification is under the jurisdiction of ASTM Committee D30 on Composite Materials and is the direct responsibility of Subcommittee D30.04 on Lamina and Laminate Test Methods.

Current edition ~~approved Sept.~~ approved June 10, 1995; 2003. Published ~~November 1995~~; August 2003. Originally ~~published as D 3410—75~~; approved in 1975. Last previous edition approved in 1995 as D 3410/D 3410M – 945.