



Standard Test Methods of Compression Testing of Metallic Materials at Room Temperature¹

This standard is issued under the fixed designation E9; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 These test methods cover the apparatus, specimens, and procedure for axial-load compression testing of metallic materials at room temperature (**Note 1**). For additional requirements pertaining to cemented carbides, see **Annex A1**.

NOTE 1—For compression tests at elevated temperatures, see Practice **E209**.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- B557** Test Methods for Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products
- E4** Practices for Force Verification of Testing Machines
- E6** Terminology Relating to Methods of Mechanical Testing
- E83** Practice for Verification and Classification of Extensometer Systems
- E111** Test Method for Young's Modulus, Tangent Modulus, and Chord Modulus
- E171** Practice for Conditioning and Testing Flexible Barrier Packaging

¹ These test methods are under the jurisdiction of ASTM Committee **E28** on Mechanical Testing and are the direct responsibility of Subcommittee **E28.04** on Uniaxial Testing.

Current edition approved Nov. 1, 2009. Published December 2009. Originally published in 1924. Last previous edition approved in 2000 as E9 -89a(2000) which was withdrawn March 2009 and reinstated in November 2009. DOI: 10.1520/E0009-09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods

E209 Practice for Compression Tests of Metallic Materials at Elevated Temperatures with Conventional or Rapid Heating Rates and Strain Rates

E251 Test Methods for Performance Characteristics of Metallic Bonded Resistance Strain Gages

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

3. Terminology

3.1 **Definitions:** The definitions of terms relating to compression testing and room temperature in Terminology **E6** and Specification **E171**, respectively, shall apply to these test methods.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 **buckling**—In addition to compressive failure by crushing of the material, compressive failure may occur by (1) elastic instability over the length of a column specimen due to nonaxiality of loading, (2) inelastic instability over the length of a column specimen, (3) a local instability, either elastic or inelastic, over a small portion of the gage length, or (4) a twisting or torsional failure in which cross sections rotate over each other about the longitudinal specimen axis. These types of failures are all termed *buckling*.

3.2.2 **column**—a compression member that is axially loaded and that may fail by buckling.

3.2.3 **radius of gyration**—the square root of the ratio of the moment of inertia of the cross section about the centroidal axis to the cross-sectional area:

$$\rho = (I/A)^{1/2} \quad (1)$$

where:

- ρ = radius of gyration,
- I = moment of inertia of the cross section about centroidal axis (for specimens without lateral support, the smaller value of I is the critical value), and
- A = cross-sectional area.