



Standard Test Methods for Rockwell Hardness of Metallic Materials^{1,2}

This standard is issued under the fixed designation E18; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

^ε¹ NOTE—A2.8.1.8 was editorially corrected in August 2017.

1. Scope*

1.1 These test methods cover the determination of the Rockwell hardness and the Rockwell superficial hardness of metallic materials by the Rockwell indentation hardness principle. This standard provides the requirements for Rockwell hardness machines and the procedures for performing Rockwell hardness tests.

1.2 This standard includes additional requirements in annexes:

Verification of Rockwell Hardness Testing Machines	Annex A1
Rockwell Hardness Standardizing Machines	Annex A2
Standardization of Rockwell Indenters	Annex A3
Standardization of Rockwell Hardness Test Blocks	Annex A4
Guidelines for Determining the Minimum Thickness of a Test Piece	Annex A5
Hardness Value Corrections When Testing on Convex Cylindrical Surfaces	Annex A6

1.3 This standard includes nonmandatory information in appendixes which relates to the Rockwell hardness test.

List of ASTM Standards Giving Hardness Values Corresponding to Tensile Strength	Appendix X1
Examples of Procedures for Determining Rockwell Hardness Uncertainty	Appendix X2

1.4 *Units*—At the time the Rockwell hardness test was developed, the force levels were specified in units of kilograms-force (kgf) and the indenter ball diameters were specified in units of inches (in.). This standard specifies the units of force and length in the International System of Units (SI); that is, force in Newtons (N) and length in millimeters (mm). However, because of the historical precedent and continued common usage, force values in kgf units and ball diameters in inch units are provided for information and much of the discussion in this standard refers to these units.

¹ These test methods are under the jurisdiction of ASTM Committee E28 on Mechanical Testing and are the direct responsibility of Subcommittee E28.06 on Indentation Hardness Testing.

Current edition approved July 1, 2017. Published July 2017. Originally approved in 1932. Last previous edition approved in 2016 as E18 – 16. DOI: 10.1520/E0018-17E01

² In this test method, the term Rockwell refers to an internationally recognized type of indentation hardness test as defined in Section 3, and not to the hardness testing equipment of a particular manufacturer.

1.5 The test principles, testing procedures, and verification procedures are essentially identical for both the Rockwell and Rockwell superficial hardness tests. The significant differences between the two tests are that the test forces are smaller for the Rockwell superficial test than for the Rockwell test. The same type and size indenters may be used for either test, depending on the scale being employed. Accordingly, throughout this standard, the term Rockwell will imply both Rockwell and Rockwell superficial unless stated otherwise.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:³

- A370 Test Methods and Definitions for Mechanical Testing of Steel Products
- A623 Specification for Tin Mill Products, General Requirements
- A623M Specification for Tin Mill Products, General Requirements [Metric]
- B19 Specification for Cartridge Brass Sheet, Strip, Plate, Bar, and Disks
- B36/B36M Specification for Brass Plate, Sheet, Strip, And Rolled Bar
- B96/B96M Specification for Copper-Silicon Alloy Plate, Sheet, Strip, and Rolled Bar for General Purposes and Pressure Vessels

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard