



Standard Test Methods for Chemical Analysis of Chromium and Ferrochromium¹

This standard is issued under the fixed designation E363; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 These test methods cover the chemical analysis of chromium and ferrochromium having chemical compositions within the following limits:

Element	Composition, %
Aluminum	0.25 max
Antimony	0.005 max
Arsenic	0.005 max
Bismuth	0.005 max
Boron	0.005 max
Carbon	9.00 max
Chromium	51.0 to 99.5
Cobalt	0.10 max
Columbium	0.05 max
Copper	0.05 max
Lead	0.005 max
Manganese	0.75 max
Molybdenum	0.05 max
Nickel	0.50 max
Nitrogen	6.00 max
Phosphorus	0.03 max
Silicon	12.00 max
Silver	0.005 max
Sulfur	0.07 max
Tantalum	0.05 max
Tin	0.005 max
Titanium	0.50 max
Vanadium	0.50 max
Zinc	0.005 max
Zirconium	0.05 max

1.2 The analytical procedures appear in the following order:

	Sections
Arsenic by the Molybdenum Blue Spectrophotometric Test Method [0.001 % to 0.005 %]	10 – 20
Lead by the Dithizone Spectrophotometric Test Method [0.001 % to 0.05 %]	21 – 31
Chromium by the Sodium Peroxide Fusion-Titrimetric Test Method [50 % to 75 %]	32 – 38

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the*

responsibility of whoever uses this standard to consult and establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. Specific hazard statements are given in Section 6 and in special "Warning" paragraphs throughout these test methods.

2. Referenced Documents

2.1 ASTM Standards:²

- A101 Specification for Ferrochromium
- A481 Specification for Chromium Metal
- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E32 Practices for Sampling Ferroalloys and Steel Additives for Determination of Chemical Composition
- E50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials
- E60 Practice for Analysis of Metals, Ores, and Related Materials by Spectrophotometry
- E135 Terminology Relating to Analytical Chemistry for Metals, Ores, and Related Materials
- E173 Practice for Conducting Interlaboratory Studies of Methods for Chemical Analysis of Metals (Withdrawn 1998)³
- E1601 Practice for Conducting an Interlaboratory Study to Evaluate the Performance of an Analytical Method

3. Terminology

3.1 For definition of terms used in this test method, refer to Terminology E135.

4. Significance and Use

4.1 These test methods for the chemical analysis of chromium metal and ferrochromium alloy are primarily intended to test such materials for compliance with compositional specifications such as Specifications A101 and A481. It is assumed that all who use these test methods will be trained analysts

¹ These test methods are under the jurisdiction of ASTM Committee E01 on Analytical Chemistry for Metals, Ores, and Related Materials and are the direct responsibility of Subcommittee E01.01 on Iron, Steel, and Ferroalloys.

Current edition approved May 1, 2016. Published June 2016. Originally approved in 1970. Last previous edition approved in 2009 as E363 – 09. DOI: 10.1520/E0363-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.