



Standard Guide to Obtainable ASTM Equivalent Penetrameter Sensitivity for Radiography of Steel Plates ¼ to 2 in. (6 to 51 mm) Thick with X-Rays and 1 to 6 in. (25 to 152 mm) Thick with Cobalt-60¹

This standard is issued under the fixed designation E592; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This guide to obtainable equivalent penetrameter sensitivity covers the minimum penetrameter thicknesses for which the image of the 1T and 2T holes is visible for a few practical radiographic conditions. The values represent near optimum sensitivity for flat steel plates. Radiographic conditions that give higher values of scatter buildup from the specimen or backscattered radiation at the image plane will give poorer sensitivity.

1.2 Eight radiographs that illustrate sensitivities obtainable with practical radiographic systems are included as adjuncts to this guide and may be obtained from ASTM.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- E746 Practice for Determining Relative Image Quality Response of Industrial Radiographic Imaging Systems
- E999 Guide for Controlling the Quality of Industrial Radiographic Film Processing
- E1025 Practice for Design, Manufacture, and Material Grouping Classification of Hole-Type Image Quality Indicators (IQI) Used for Radiology

¹ This guide is under the jurisdiction of ASTM Committee E07 on Nondestructive Testing and is the direct responsibility of Subcommittee E07.02 on Reference Radiological Images.

Current edition approved June 1, 2015. Published June 2015. Originally approved in 1977. Last previous edition approved in 2009 as E592 - 99(2009)^{ε1}. DOI: 10.1520/E0592-99R15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

dicators (IQI) Used for Radiology

E1316 Terminology for Nondestructive Examinations

E1742 Practice for Radiographic Examination

E1735 Test Method for Determining Relative Image Quality of Industrial Radiographic Film Exposed to X-Radiation from 4 to 25 MeV

E1815 Test Method for Classification of Film Systems for Industrial Radiography

2.2 ISO Standard:

ISO 7004 Photography—Industrial Radiographic Films—Determination of ISO Speed, ISO Average Gradient, and ISO Gradients G2 and G4 When Exposed to X- and Gamma-Radiation³

2.3 Military Standard:

NAVSEA Technical Publication T9074-AS-GIB-010/271 Requirements for Nondestructive Testing Methods

2.4 ASTM Adjuncts:

Guide for Equivalent Penetrameter Sensitivity Between X-Rays and Cobalt-60⁴

3. Terminology

3.1 *Definitions:* For definitions of terms used in this standard, refer to Terminology E1316, Section D.

4. Significance and Use

4.1 A key consideration with any radiographic system is its contrast resolution and spatial resolution capability (that is, sensitivity). The degree of obtainable sensitivity with a given system is dependent upon several radiographic parameters such as source energy level, film system class, type and thickness of intensifying screens, exposure (density), etc. This guide permits the user to estimate the degree of sensitivity that may be obtained with X-rays and cobalt-60 gamma rays when using a prescribed set of radiographic parameters. This guide may also be used in conjunction with Test Methods E746 or E1735 to provide a basis for developing data for evaluation of a user's

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

⁴ Available from ASTM Headquarters. Order RRE0592.

*A Summary of Changes section appears at the end of this standard