



Standard Test Method for Measuring Pavement Macrotexture Depth Using a Volumetric Technique¹

This standard is issued under the fixed designation E965; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method describes a procedure for determining the average depth of pavement surface macrotexture (see 3.1) ⁽¹⁾² by careful application of a known volume of material on the surface and subsequent measurement of the total area covered. The technique is designed to provide an average depth value of only the pavement macrotexture and is considered insensitive to pavement microtexture characteristics.

1.2 The results obtained using this procedure to determine average pavement macrotexture depths do not necessarily agree or correlate directly with those obtained by other pavement macrotexture measuring methods **(1-5)**.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:³

D1155 Test Method for Roundness of Glass Spheres
E178 Practice for Dealing With Outlying Observations
E867 Terminology Relating to Vehicle-Pavement Systems

¹ This test method is under the jurisdiction of ASTM Committee E17 on Vehicle - Pavement Systems and is the direct responsibility of Subcommittee E17.23 on Surface Characteristics Related to Tire Pavement Slip Resistance.

Current edition approved May 1, 2015. Published June 2015. Originally approved in 1983. Last previous edition approved in 2006 as E965 – 96 (2006) which was withdrawn in January 2015 and reinstated in May 2015. DOI: 10.1520/E0965-15.

² The boldface numbers in parentheses refer to the list of references at the end of this test method.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. Terminology

3.1 Terminology used in this standard conforms to Terminology **E867**.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *pavement macrotexture*—the deviations of a pavement surface from a true planar surface with the characteristic dimensions of wavelength and amplitude from 0.5 mm up to those that no longer affect tire-pavement interaction.

4. Summary of Test Method

4.1 The standard materials and test apparatus consist of a quantity of uniform material, a container of known volume, a suitable wind screen or shield, brushes for cleaning the pavement surface, a flat disk for spreading the material on the surface, and a ruler or other measuring device for determining the area covered by the material. A laboratory balance is also recommended for further ensuring consistent amounts for each measurement sample.

4.2 The test procedure involves spreading a known volume of material on a clean and dry pavement surface, measuring the area covered, and subsequently calculating the average depth between the bottom of the pavement surface voids and the tops of surface aggregate particles. This measurement of pavement surface texture depth reflects the pavement macrotexture characteristics **(1, 5)**.

NOTE 1—In spreading the material specified in this test method, the surface voids are completely filled flush to the tips of the surrounding aggregate particles. This test method is not considered suitable for use on grooved surfaces or pavements with large (≥ 1.0 in. (25 mm)) surface voids.

5. Significance and Use

5.1 This test method is suitable for research and development purposes and for field tests to determine the average macrotexture depth of a pavement surface. The knowledge of pavement macrotexture depth serves as a tool in characterizing the pavement surface texture. When used in conjunction with other physical tests, the macrotexture depth values derived from this test method may be used to determine the pavement skid resistance capability and the suitability of paving materials or finishing techniques. When used with other tests, care should be taken that all tests are applied at the same location.