



Standard Guide for Electrolytic Polishing of Metallographic Specimens¹

This standard is issued under the fixed designation E1558; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide deals with electrolytic polishing as a means of preparation of specimens for metallographic purposes. Procedures are described for polishing a variety of metals.

NOTE 1—References (1-133)² on electrolytic polishing will provide the reader with specific information beyond the scope of this guide.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific safety precautions are described in Section 5 and 6.3.1.

2. Referenced Documents

2.1 *ASTM Standards:*³

E7 Terminology Relating to Metallography

E407 Practice for Microetching Metals and Alloys

3. Terminology

3.1 *Definitions*—All terms used in this guide are either defined in Terminology E7 or are discussed in 3.2.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *electrolytic polish (electropolish)*—A method of polishing metals and alloys in which material is removed from the surface by making the metal the anode in an electrolytic bath.

4. Significance and Use

4.1 *Advantages of Electrolytic Polishing:*

4.1.1 For some metals, a high quality surface finish can be produced that is equivalent to, or better than, that which can be obtained by mechanical methods.

4.1.2 Once procedures have been established, satisfactory results can be obtained rapidly with reproducibility.

4.1.3 There can be a marked saving of time if many specimens of the same material are polished sequentially.

4.1.4 Electropolishing a selected area on the surface of a relatively large metal part can be accomplished nondestructively, that is, without the need for sectioning to remove a piece.

4.1.5 Soft, single-phase metals, which may be difficult to polish by mechanical methods, may be successfully electropolished.

4.1.6 The true microstructure of a specimen can be obtained because artifacts (such as disturbed metal, scratches, and mechanical twins) produced on the surface, even by careful grinding and mechanical polishing operations, can be removed. These features are important in low-load hardness testing, X-ray diffraction studies, and in electron microscopy, where higher resolution puts a premium on undistorted metal surfaces.

4.1.7 After electropolishing is completed, etching can often be accomplished by reducing the voltage (generally to about one-tenth that required for polishing) for a short time before it is turned off.

NOTE 2—Not all electropolishing solutions produce good etching results.

4.2 *Disadvantages of Electrolytic Polishing:*

4.2.1 Many of the chemical mixtures used in electropolishing are poisonous or dangerous if not properly handled (see Section 5). These hazards are similar to those involved in the mixing and handling of etchants, see Test Methods E407.

4.2.2 In multi-phase alloys, the polishing rate of each phase may be different. The result may be a non-planar surface.

4.2.3 Electropolished surfaces may be slightly undulated rather than perfectly planar and, therefore, may not be suitable for examination at all magnifications.

4.2.4 The rate of polishing in areas adjacent to various inhomogeneities, such as nonmetallic inclusions and voids, is usually greater than that in the surrounding matrix and tends to exaggerate the size of the inclusions and voids.

¹ This guide is under the jurisdiction of ASTM Committee E04 on Metallography and is the direct responsibility of Subcommittee E04.01 on Specimen Preparation. Current edition approved Oct. 1, 2014. Published December 2014. Originally approved in 1993. Last previous edition approved in 2009 as E1558 – 09. DOI: 10.1520/E1558-09R14.

² The **boldface** numbers in parentheses refer to the references at the end of this standard.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.