



Standard Test Method for Sheet Resistance of Silicon Epitaxial, Diffused, Polysilicon, and Ion-implanted Layers Using an In-Line Four-Point Probe with the Single-Configuration Procedure¹

This standard is issued under the fixed designation F 374; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the direct measurement of the average sheet resistance of thin layers of silicon with diameters greater than 15.9 mm (0.625 in.) which are formed by epitaxy, diffusion, or implantation onto or below the surface of a circular silicon wafer having the opposite conductivity type from the thin layer to be measured or by the deposition of polysilicon over an insulating layer. Measurements are made at the center of the wafer using a single-configuration of the four-probe, that is, with the current being passed through the outer pins and the resulting potential difference being measured with the inner pins.

1.2 This test method is known to be applicable on films having thickness at least 0.2 μm. It can be used to measure sheet resistance in the range 10 to 5000 Ω, inclusive.

1.2.1 The principle of the test method can be extended to cover lower or higher values of sheet resistance; however, the precision of the method has not been evaluated for sheet resistance ranges other than those given in 1.2.

NOTE 1—The minimum value of the diameter is related to tolerances on the accuracy of the measurement through the geometric correction factor. The minimum layer thickness is related to danger of penetration of the probe tips through the layer during measurement.

1.3 Procedures for preparing the specimen, for measuring its size, and for determining the temperature of the specimen during the measurement are also given. Abbreviated tables of correction factors appropriate to circular geometry are included with the method so that appropriate calculations can be made conveniently.

NOTE 2—The principles of this test method are also applicable to other semiconductor materials, but neither the appropriate conditions nor the expected precision have been determined. Other geometries can also be measured, but only comparative measurements using similar geometrical conditions should be used unless proper geometrical correction factors are known.

NOTE 3—Some relaxations of test conditions are mentioned in order to assist in applying the principles of the method to nonreferee applications,

for which a complete nonreferee method has not yet been developed. The relaxed test conditions given are consensus conditions only and their effect on measurement precision and accuracy has not been explored.

1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific hazard statements are given in Section 9.

2. Referenced Documents

2.1 ASTM Standards:

D 5127 Guide for Ultra Pure Water Used in the Electronics and Semiconductor Industry²

E 1 Specification for ASTM Thermometers³

F 42 Test Method for Conductivity Type of Extrinsic Semiconducting Materials⁴

F 1529 Test Method for Sheet Resistance Uniformity Evaluation by In-Line Four-Point Probe with the Dual-Configuration Procedure⁴

2.2 SEMI Standard:

C 3.15 Specifications for Nitrogen Gas⁵

C 28 Specification for Hydrofluoric Acid⁵

C 31 Specification for Methanol⁵

3. Terminology

3.1 Definitions:

3.1.1 *four-point probe*—an electrical probe arrangement for determining the resistivity of a material in which separate pairs of contacts are used (1) for passing current through the specimen and (2) measuring the potential drop caused by the current.

3.1.1.1 *Discussion*—It may consist of a unitized probe head holding all four probes or it may have each of the four individual probes attached to a separate cantilevered arm.

¹ This test method is under the jurisdiction of ASTM Committee F01 on Electronics and is the direct responsibility of Subcommittee F01.06 on Silicon Materials and Process Control.

Current edition approved Dec. 10, 2000. Published February 2001. Originally published as F 374 – 74 T. Last previous edition F 374 – 00.

² *Annual Book of ASTM Standards*, Vol 11.01.

³ *Annual Book of ASTM Standards*, Vol 14.03.

⁴ *Annual Book of ASTM Standards*, Vol 10.05.

⁵ Available from the Semiconductor Equipment and Materials Institute, 625 Ellis St., Suite 212, Mountain View, CA 94043.