



Standard Test Method for Outdoor Evaluation of Tire Sidewall Component Cracking Resistance¹

This standard is issued under the fixed designation F724; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers procedures for evaluating passenger car tires for sidewall component integrity and cracking resistance, using an outdoor roadwheel.

1.2 This test method evaluates the resistance of tire sidewalls to dynamic weathering, atmospheric ozone cracking, fatigue cracking, or openings of splices within, or of junctures between, sidewall components and cracking at molded sidewall elements.

1.3 This test method is useful for evaluating tire black sidewalls, white, or other colored, sidewalls, and coverstrips.

1.4 This test method is limited to comparative performance testing between a “control” sidewall component or assembly and one or more experimental alternatives that are built onto the same tire (“multisection”) or onto tires that are identical in all respects other than the sidewall variation.

1.5 This test method is not applicable to evaluation of sidewall resistance to abrasion, as may be experienced in severe cornering or curb scuffing.

1.6 The values stated in SI units are to be regarded as the standard.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific precaution statements, see 5.2.

2. Referenced Documents

2.1 ASTM Standards:²

¹ This test method is under the jurisdiction of ASTM Committee F09 on Tires and is the direct responsibility of Subcommittee F09.30 on Laboratory (Non-Vehicular) Testing.

Current edition approved Jan. 1, 2016. Published February 2016. Originally approved in 1981. Last previous edition approved in 2010 as F724 – 94a (2010) ^{ϵ 1}. DOI: 10.1520/F0724-94AR16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

D518 Test Method for Rubber Deterioration—Surface Cracking (Withdrawn 2007)³

D1149 Test Methods for Rubber Deterioration—Cracking in an Ozone Controlled Environment

D1171 Test Method for Rubber Deterioration—Surface Ozone Cracking Outdoors (Triangular Specimens)

D3395 Test Methods for Rubber Deterioration—Dynamic Ozone Cracking in a Chamber (Withdrawn 2007)³

F538 Terminology Relating to the Characteristics and Performance of Tires

3. Terminology

3.1 Definitions:

3.1.1 *black sidewall, n*—a sidewall on which only black compounds comprise the outer visible surface of a tire. **F538**

3.1.2 *clinch strip, n*—high-modulus or high-hardness compound applied between the carcass and the sidewall in the bead area to reinforce the bead. **F538**

3.1.3 *coverstrip, n*—a thin layer of black compound that covers the unexposed white sidewall portion of a finished tire. **F538**

3.1.4 *crazing, n*—minute, closely grouped, generally superficial cracks that usually result from light-activated oxidation. **F538**

3.1.5 *flex cracking, v*—cracking primarily caused by application of mechanical stress-strain cycling. **F538**

3.1.6 *junction, n*—the interface between two different tire components or different compounds within the same component. **F538**

3.1.7 *junction cracking, n*—a crack with opening originating at a junction between two components. **F538**

3.1.8 *junction opening, n*—a separation developing in a junction. **F538**

3.1.9 *rim strip, n*—a layer of compound, with or without fabric reinforcement, that is applied at the bead to protect the carcass plies against damage from mounting tools and from rim chafing during service. **F538**

³ The last approved version of this historical standard is referenced on www.astm.org.