



Designation: F735 – 17

Standard Test Method for Abrasion Resistance of Transparent Plastics and Coatings Using the Oscillating Sand Method¹

This standard is issued under the fixed designation F735; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method determines the resistance of transparent plastics and transparent coatings utilized in windows or viewing ports, to surface abrasion using oscillating sand.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.2.1 *Exception*—The inch-pound units in parentheses are provided for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C136 Test Method for Sieve Analysis of Fine and Coarse Aggregates

D618 Practice for Conditioning Plastics for Testing

D1003 Test Method for Haze and Luminous Transmittance of Transparent Plastics

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods

¹ This test method is under the jurisdiction of ASTM Committee F07 on Aerospace and Aircraft and is the direct responsibility of Subcommittee F07.08 on Transparent Enclosures and Materials.

Current edition approved June 1, 2017. Published July 2017. Originally approved in 1981. Last previous edition approved in 2011 as F735 – 11. DOI: 10.1520/F0735-17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

3. Summary of Test Method

3.1 The test method consists of measuring and recording the haze and light transmission of a test specimen, mounting the specimen so that it forms part of the bottom tray (sand cradle), covering the specimen with abrading media, and subjecting the cradle to a specific number of oscillations. After exposure to the abrasion, the haze and light transmission are remeasured to determine any change in these values.

3.2 At the stroke velocity specified in this test method, the entire mass of sand shifts significantly within the sand cradle because of its inertia; therefore the relative motion between sand and specimen at the interface is large.

3.3 The thickness or height of the sand resting on top of the test specimen remains relatively constant during the motion of the cradle. Therefore, the average pressure of the sand also remains constant, giving highly reproducible results over the entire surface of the test specimen.

3.4 The degree of abrasion is measured by the amount of change in luminous transmission and haze after exposure to the test.

4. Significance and Use

4.1 Plastic materials, when used as transparencies, covers, or enclosures, are subject to wiping, cleaning, or other types of rubbing actions that cause abrasion. It is the intent of this test method to provide a means of estimating the resistance of such materials to this type and degree of abrasion.

5. Apparatus

5.1 *Abrader*—The abrader consists of a specimen holder, sand cradle, drive mechanism, and counter. One such example is shown in **Fig. 1**.

5.1.1 The specimen holder shall have a cutout approximately 100 by 100 mm (4 by 4 in.) to receive the specimen. Alternative specimen holders can be used to test other specimen sizes as long as they can be used within the testing limitations defined in this test method.

5.1.2 The specimen holder forms the bottom of the sand cradle.

*A Summary of Changes section appears at the end of this standard