



Designation: F 970 – 9900

Standard Test Method for Static Load Limit¹

This standard is issued under the fixed designation F 970; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method is intended for use in determining the recovery properties of resilient floor covering after long-term indentation test, 24 h under the load specified in the detail specification. The reported value, residual compression, is the depth of hole remaining 24 h after removal of the specified load.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

E 171 Specification for Standard Atmospheres for Conditioning and Testing Materials²

¹ This test method is under the jurisdiction of ASTM Committee F-6 F06 on Resilient Floor Coverings and is the direct responsibility of Subcommittee F06.30 on Test Methods—Performance.

Current edition approved July Sept. 10, 1999; 2000. Published August 1999; November 2000. Originally published as F 970–87. Last previous edition F 970–98. F 970–99.