



Standard Specification for Coextruded Composite Drain, Waste, and Vent Pipe (DWV)¹

This standard is issued under the fixed designation F1499; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers coextruded composite drain, waste, and vent pipe (DWV). The pipe is produced in Schedule 40 IPS sizes by a coextrusion die system, in which the concentric layers are formed and combined before exiting the die.

1.1.1 Coextruded composite drain, waste, and vent pipe, DWV, by definition, is permitted to be produced with two or more layers. The outer layer shall be ABS. The middle layer is permitted to be thermally foamed PVC or solid PVC or a blend of rework material, as specified in the rework material section. The inner layer is permitted to be solid PVC or ABS, or a blend of rework material as specified in the rework material section.

1.1.2 The function of this specification is to provide standardization of product, technical data, and serve as a purchasing guide.

1.2 DWV is permitted to be produced utilizing a two layer or three layer coextrusion die.

1.3 Materials that do not meet the requirements of the material section are excluded.

1.4 Pipe produced to this specification is permitted to be joined using molded fittings meeting the requirements of Specification [D2661](#) or Specification [F628](#). The fitting patterns must comply with Specification [D3311](#).

1.5 Pipe produced to this specification is permitted to be perforated in accordance with any specified standard or by agreement between the purchaser and the supplier.

1.6 Pipe produced to this specification is permitted to be belled for joining by solvent cementing or belled for joining by an elastomeric seal (gasket), in accordance with any specified standard or by agreement between the purchaser and the supplier.

1.7 Recommendations for storage, joining, and installation are provided in [Appendix X1](#), [Appendix X2](#), and [Appendix X3](#), respectively.

1.8 The values stated in inch-pound units are to be regarded as the standard. The SI units given in parentheses are for information only.

1.9 The text of this specification references notes, footnotes, and appendixes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of this specification.

1.10 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.11 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—Specifications related to this specification are as follows: Specifications [D2661](#), [D2665](#), [F628](#), and [F891](#).

2. Referenced Documents

2.1 The following standards contain provisions that, though referenced in this specification, constitute provisions of this specification. All standards are subject to revision and parties using this specification, shall reference the most recent edition of the standards listed as follows:

2.2 ASTM Standards:²

[D618 Practice for Conditioning Plastics for Testing](#)

[D696 Test Method for Coefficient of Linear Thermal Expansion of Plastics Between –30°C and 30°C with a Vitreous Silica Dilatometer](#)

[D883 Terminology Relating to Plastics](#)

[D1600 Terminology for Abbreviated Terms Relating to Plastics](#)

[D1784 Specification for Rigid Poly\(Vinyl Chloride\) \(PVC\) Compounds and Chlorinated Poly\(Vinyl Chloride\) \(CPVC\) Compounds](#)

¹ This specification is under the jurisdiction of ASTM Committee [F17](#) on Plastic Piping Systems and is the direct responsibility of Subcommittee [F17.63](#) on DWV.

Current edition approved April 1, 2012. Published April 2012. Originally published as approved in 1994. Last previous edition approved in 2008 as F1499 – 01(2008). DOI: 10.1520/F1499-12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.