



Designation: F2059 – 17

Standard Test Method for Laboratory Oil Spill Dispersant Effectiveness Using the Swirling Flask¹

This standard is issued under the fixed designation F2059; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This test method covers the procedure to determine the effectiveness of oil spill dispersants on various oils in the laboratory. This test method is not applicable to other chemical agents nor to the use of such products or dispersants in open waters.

1.2 This test method covers the use of the swirling flask test apparatus and does not cover other apparatuses nor are the analytical procedures described in this report directly applicable to such procedures.

1.3 The test results obtained using this test method are intended to provide baseline effectiveness values used to compare dispersants and oil types under conditions analogous to those used in the test.

1.4 The test results obtained using this test method are effectiveness values that should be cited as test values derived from this standard test. Dispersant effectiveness values do not directly relate to effectiveness at sea or in other apparatuses. Actual effectiveness at sea is dependant on sea energy, oil state, temperature, salinity, actual dispersant dosage, and amount of dispersant that enters the oil.

1.5 The decision to use or not use a dispersant on an oil should not be based solely on this or any other laboratory test method.

1.6 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.8 *This international standard was developed in accordance with internationally recognized principles on standard-*

ization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Summary of Test Method

2.1 Dispersant is pre-mixed with oil and placed on water in a test vessel. The test vessel is agitated on a moving table shaker. At the end of the shaking period, a settling period is specified and then a sample of water taken. The oil in the water column is extracted from the water using a dichloromethane solvent and analyzed using gas chromatography.

2.2 The extract is analyzed for oil using a gas chromatograph equipped with a flame ionization detector, (GC-FID). Quantification is by means of the internal standard method. Effectiveness values are derived by comparison with a calibrated set of effectiveness values obtained at the same time and by the same method.

3. Significance and Use

3.1 A standard test is necessary to establish a baseline performance parameter so that dispersants can be compared, a given dispersant can be compared for effectiveness on different oils, and at different oil weathering stages, and batches of dispersant or oils can be checked for effectiveness changes with time or other factors.

3.2 Dispersant effectiveness varies with oil type, sea energy, oil conditions, salinity, and many other factors. Test results from this test method form a baseline, but are not to be taken as the absolute measure of performance at sea. Actual field effectiveness could be more or less than this value.

3.3 Many dispersant tests have been developed around the world. This test has been developed over many years using findings from world-wide testing to use standardized equipment, test procedures, and to overcome difficulties noted in other test procedures.

4. Interferences and Sources of Error

4.1 Interferences can be caused by contaminants, particularly residual oil or surfactants in solvents, on glassware, and other sample processing apparatus that lead to discrete artifacts

¹ This test method is under the jurisdiction of ASTM Committee F20 on Hazardous Substances and Oil Spill Response and is the direct responsibility of Subcommittee F20.13 on Treatment.

Current edition approved April 15, 2017. Published April 2017. Originally approved in 2000. Last previous edition approved in 2012 as F2059 – 06(2012) ^{ϵ 1}. DOI: 10.1520/F2059-17