



Standard Test Method for Unsteady-State Heat Transfer Evaluation of Flame Resistant Materials for Clothing with Continuous Heating¹

This standard is issued under the fixed designation F2700; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method measures the non-steady state heat transfer through flame resistant materials for clothing subjected to a continuous, combined convective and radiant heat exposure.

1.1.1 This test method is not applicable to materials that are not flame resistant.

NOTE 1—The determination of a material's flame resistance shall be made prior to testing and done according to the applicable performance or specification standard, or both, for the material's end-use.

1.1.2 This test method does not predict a material's skin burn injury performance from the specified thermal energy exposure. It does not account for the thermal energy contained in the test specimen after the exposure has ceased.

NOTE 2—See [Appendix X4](#) for additional information regarding this test method and predicted skin burn injury.

1.2 This test method is used to measure and describe the response of materials, products, or assemblies to heat under controlled conditions, but does not by itself incorporate all factors required for fire hazard or fire risk assessment of the materials, products, or assemblies under actual fire conditions.

1.3 The values stated in SI units are to be regarded as standard. The values given in parentheses are mathematical conversions to inch-pound or other units that are commonly used for thermal testing.

1.4 *This standard does not purport to address the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

¹ This test method is under the jurisdiction of ASTM Committee F23 on Personal Protective Clothing and Equipment and is the direct responsibility of Subcommittee F23.80 on Flame and Thermal.

Current edition approved June 1, 2013. Published June 2013. Originally approved in 2008. Last previous edition approved in 2008 as F2700 - 08. DOI: 10.1520/F2700-08R13.

2. Referenced Documents

2.1 *ASTM Standards*:²

D123 Terminology Relating to Textiles

D1776 Practice for Conditioning and Testing Textiles

D1777 Test Method for Thickness of Textile Materials

D3776 Test Methods for Mass Per Unit Area (Weight) of Fabric

E457 Test Method for Measuring Heat-Transfer Rate Using a Thermal Capacitance (Slug) Calorimeter

F1494 Terminology Relating to Protective Clothing

F2703 Test Method for Unsteady-State Heat Transfer Evaluation of Flame Resistant Materials for Clothing with Burn Injury Prediction

3. Terminology

3.1 *Definitions*:

3.1.1 *breakopen, n*—in testing thermal protective materials, a material response evidenced by the formation of a hole in the test specimen during the thermal exposure that may result in the exposure energy in direct contact with the heat sensor.

3.1.1.1 *Discussion*—The specimen is considered to exhibit breakopen when a hole is produced as a result of the thermal exposure that is at least 3.2 cm² (0.5 in.²) in area or at least 2.5 cm (1.0 in.) in any dimension. Single threads across the opening or hole do not reduce the size of the hole for the purposes of this test method.

3.1.2 *charring, n*—the formation of a carbonaceous residue as the result of pyrolysis or incomplete combustion.

3.1.3 *dripping, n*—a material response evidenced by flowing of the polymer.

3.1.4 *embrittlement, n*—the formation of a brittle residue as a result of pyrolysis or incomplete combustion.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.