



Standard Test Method for Exfoliation Corrosion Susceptibility in 2XXX and 7XXX Series Aluminum Alloys (EXCO Test)¹

This standard is issued under the fixed designation G34; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers a procedure for constant immersion exfoliation corrosion (EXCO) testing of high-strength 2XXX and 7XXX series aluminum alloys.

NOTE 1—This test method was originally developed for research and development purposes; however, it is referenced, in specific material specifications, as applicable for evaluating production material (refer to Section 14 on Precision and Bias).

1.2 This test method applies to all wrought products such as sheet, plate, extrusions, and forgings produced from conventional ingot metallurgy process.

1.3 This test method can be used with any form of specimen or part that can be immersed in the test solution.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

D1193 Specification for Reagent Water

E3 Guide for Preparation of Metallographic Specimens

G15 Terminology Relating to Corrosion and Corrosion Testing (Withdrawn 2010)³

G112 Guide for Conducting Exfoliation Corrosion Tests in Aluminum Alloys

¹ This test method is under the jurisdiction of ASTM Committee G01 on Corrosion of Metals and is the direct responsibility of Subcommittee G01.05 on Laboratory Corrosion Tests.

Current edition approved May 1, 2013. Published July 2013. Originally approved in 1972. Last previous edition approved in 2007 as G34–01 (2007). DOI: 10.1520/G0034-01R13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

2.2 ASTM Adjuncts:

Illustrations (Enlarged Glossy Prints)⁴

3. Terminology

3.1 Definitions:

3.1.1 *exfoliation*—corrosion that proceeds laterally from the sites of initiation along planes parallel to the surface, generally at grain boundaries, forming corrosion products that force metal away from the body of the material giving rise to a layered appearance (Terminology G15).

4. Summary of Test Method

4.1 This test method provides an accelerated exfoliation corrosion test for 2XXX and 7XXX series aluminum alloys that involves the continuous immersion of test materials in a solution containing 4 M sodium chloride, 0.5 M potassium nitrate, and 0.1 M nitric acid at $25 \pm 3^\circ\text{C}$ ($77 \pm 5^\circ\text{F}$). The susceptibility to exfoliation is determined by visual examination, with performance ratings established by reference to standard photographs.

5. Significance and Use

5.1 This test method was originally developed for research and development purposes; however, it is referenced, in specific material specifications, as applicable for evaluating production material (refer to Section 14 on Precision and Bias).

5.2 Use of this test method provides a useful prediction of the exfoliation corrosion behavior of these alloys in various types of outdoor service, especially in marine and industrial environments.⁵ The test solution is very corrosive and represents the more severe types of environmental service, excluding, of course, unusual chemicals not likely to be encountered in natural environments.

⁴ Available from ASTM International Headquarters. Order Adjunct No. ADJG003402. Original adjunct produced in 1980.

⁵ Ketcham, S. J., and Jeffrey, P. W., "Exfoliation Corrosion Testing of 7178 and 7075 Aluminum Alloys" (Report of ASTM G01.05 Interlaboratory Testing Program in Cooperation with the Aluminum Association); and Sprowls, D. O., Walsh, J. D., and Shumaker, M. B., "Simplified Exfoliation Testing of Aluminum Alloys," *Localized Corrosion—Cause of Metal Failure*, ASTM STP 516, ASTM, 1972.