



Standard Test Method for Erosion of Solid Materials by Cavitating Liquid Jet¹

This standard is issued under the fixed designation G134; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Updated Section 3 to reflect Terminology G40–10b editorially in December 2010.

1. Scope

1.1 This test method covers a test that can be used to compare the cavitation erosion resistance of solid materials. A submerged cavitating jet, issuing from a nozzle, impinges on a test specimen placed in its path so that cavities collapse on it, thereby causing erosion. The test is carried out under specified conditions in a specified liquid, usually water. This test method can also be used to compare the cavitation erosion capability of various liquids.

1.2 This test method specifies the nozzle and nozzle holder shape and size, the specimen size and its method of mounting, and the minimum test chamber size. Procedures are described for selecting the standoff distance and one of several standard test conditions. Deviation from some of these conditions is permitted where appropriate and if properly documented. Guidance is given on setting up a suitable apparatus, test and reporting procedures, and the precautions to be taken. Standard reference materials are specified; these must be used to verify the operation of the facility and to define the normalized erosion resistance of other materials.

1.3 Two types of tests are encompassed, one using test liquids which can be run to waste, for example, tap water, and the other using liquids which must be recirculated, for example, reagent water or various oils. Slightly different test circuits are required for each type.

1.4 This test method provides an alternative to Test Method G32. In that method, cavitation is induced by vibrating a submerged specimen at high frequency (20 kHz) with a specified amplitude. In the present method, cavitation is generated in a flowing system so that both the jet velocity and the downstream pressure (which causes the bubble collapse) can be varied independently.

1.5 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

A276 Specification for Stainless Steel Bars and Shapes
B160 Specification for Nickel Rod and Bar
B211 Specification for Aluminum and Aluminum-Alloy Rolled or Cold Finished Bar, Rod, and Wire
D1193 Specification for Reagent Water
E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method
G32 Test Method for Cavitation Erosion Using Vibratory Apparatus
G40 Terminology Relating to Wear and Erosion
G73 Test Method for Liquid Impingement Erosion Using Rotating Apparatus

2.2 ASTM Adjuncts:

Manufacturing Drawings of the Apparatus³

3. Terminology

3.1 See Terminology G40 for definitions of terms relating to cavitation erosion. For convenience, definitions of some important terms used in this test method are reproduced below.

3.2 Definitions:

3.2.1 *cavitation, n*—the formation and subsequent collapse, within a liquid, of cavities or bubbles that contain vapor or a mixture of vapor and gas.

3.2.1.1 *Discussion*—Cavitation originates from a local decrease in hydrostatic pressure in the liquid, usually produced by motion of the liquid (see **flow cavitation**) or of a solid

¹ This test method is under the jurisdiction of ASTM Committee G02 on Wear and Erosion and is the direct responsibility of Subcommittee G02.10 on Erosion by Solids and Liquids.

Current edition approved Dec. 1, 2010. Published December 2010. Originally approved in 1995. Last previous edition approved in 2006 as G134–95(2006). DOI: 10.1520/G0134-95R10E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from ASTM International Headquarters. Order Adjunct No. ADJG0134.